

ABSTRACT OF THE DISCLOSURE

In crystallizing an amorphous silicon film by illuminating it with linear pulse laser beams having a normal-distribution type beam profile or a similar beam profile, the linear pulse laser beams are applied in an overlapped manner. There can be obtained effects similar to those as obtained by a method in which the laser illumination power is gradually increased and then decreased in a step-like manner in plural scans.